

## TECHNICAL CHARACTERISTICS OF PRODUCT

The characteristics of the product specified in this technical report meet the specification and test methods according to norm ANSI A 137, ASTM, DIN 51130 and AS 4586 requirements.

### PRODUCT SPECIFICATION

|                                 |                                  |
|---------------------------------|----------------------------------|
| <b>Reference</b>                | <b>PULPIS CREMA PO 29,4X29,4</b> |
| <b>Product Code</b>             | 8034563                          |
| <b>Nominal Size (N)</b>         | 29,4 cm x 29,4 cm                |
| <b>Work Size (W)</b>            | 293,9 mm x 293,9 mm              |
| <b>Thickness</b>                | 10,5 mm                          |
| <b>Water Absorption</b>         | Bla ( $\leq 0,50\%$ )            |
| <b>Shade Variation</b>          | V3                               |
| <b>Application Joint</b>        | 2,0 mm                           |
| <b>Coverage Area</b>            | 1,04 m <sup>2</sup> /cx          |
| <b>Number of pieces per box</b> | 12                               |
| <b>Usage Recommendation</b>     | LB                               |

Check if the product is adequate for the planned installation area according to the room application table:

| CODE | APPLICATION ROOM   |
|------|--|
| LA   | Residencial bathrooms.   |
| LB   | Residencial areas, bedrooms and kitchens with no access to the street and LA spaces.   |
| LC   | Commercial areas without access to the street, garages, porches and residencial areas with access to the street, and LB and LA spaces. |
| LD   | Commercial areas with access to the street and LA, LB, and LA spaces.  |
| LE   | Sidewalks and outside flat areas and LD, LC, LB and LA spaces.   |
| LP   | Pools.   |
| LF   | Facades.   |

### PHYSICAL PROPERTIES

|                             |            |
|-----------------------------|------------|
| Breaking strength (lbf)     | $\geq 250$ |
| Water Absorption (%)        | $\leq 0,5$ |
| Visible abrasion Resistance | 4          |

---

### ANTISLIP CLASSIFICATIONS

---

Angle: Oil: 0°  
Dry: 25°  
Classification: Unclassified

---

*Test method according to norm DIN 51130 (R)*

---

### SLIP RESISTANCE CLASSIFICATION – METHOD PENDULUM TEST

---

Average (USRV): 17  
Classification: P1

---

*Test method according to norm AS 4586 – Anexo A.*

---

### CHEMICAL PROPERTIES

---


Chemical Resistance Class E  
Stain Resistance Class A

---

#### Attention:


- Sand may produce scratches on any type of surface covering (stone, wood, vinyl or ceramic tiles). Therefore, ceramic tiles are not warranted against scratches, especially concerning glossy surface products.
- Special care is recommended during the application and its use
- In residential areas, we recommend to protect the base of furniture and appliances.
- Product manufactured by the wet process.
- Product with Class I combustibility, according to NBR 15575.

May 02, 2017.  
Cocal do Sul – SC – Brazil



---

Sergio Pereira Ruzza  
Gerente de Tecnologia Cerâmica



---

Angela Waterkemper Vieira  
Analista Desenvolvimento de Processos