

TECHNICAL CHARACTERISTICS OF PRODUCT

The characteristics of the product specified in this technical report meet the specification and test methods according to norm ANSI A 137, ASTM, DIN 51130 and AS 4586 requirements.

PRODUCT SPECIFICATION

| | |
|---------------------------------|--------------------------------|
| Reference | MINIMUM CHUMBO NA 60X60 |
| Product Code | 8021655 |
| Nominal Size (N) | 60 cm x 60 cm |
| Work Size (W) | 600,0 mm x 600,0 mm |
| Thickness | 9,5 mm |
| Water Absorption | Bla |
| Shade Variation | V1 |
| Application Joint | 2,0 mm |
| Coverage Area | 1,44 m ² /cx |
| Number of pieces per box | 4 |
| Usage Recommendation | LD |

Check if the product is adequate for the planned installation area according to the room application table:

| CODE | APPLICATION ROOM |
|------|--|
| LA | Residencial bathrooms. |
| LB | Residential areas, bedrooms and kitchens with no access to the street and LA spaces. |
| LC | Commercial areas without access to the street, garages, porches and residential areas with access to the street, and LB and LA spaces. |
| LD | Commercial areas with access to the street and LA, LB, and LA spaces. |
| LE | Sidewalks and outside flat areas and LD, LC, LB and LA spaces. |
| LP | Pools. |
| LF | Facades. |

PHYSICAL PROPERTIES

| | |
|-------------------------|-------|
| Breaking strength (lbf) | ≥ 250 |
| Water Absorption (%) | ≤ 0,5 |

ANTISLIP CLASSIFICATIONS

Angle: Oil: 15°
Dry: 25°
Classification: R10

Test method according to norm DIN 51130 (R)

SLIP RESISTANCE CLASSIFICATION – METHOD PENDULUM TEST

Average (USRV): 24
Classification: P1

Test method according to norm AS 4586 – Anexo A.


CHEMICAL PROPERTIES

| | |
|---------------------|---------|
| Chemical Resistance | Class C |
| Stain Resistance | Class B |

Attention:

- Sand may produce scratches on any type of surface covering (stone, wood, vinyl or ceramic tiles). Therefore, ceramic tiles are not warranted against scratches, especially concerning glossy surface products.
- Special care is recommended during the application and its use
- In residential areas, we recommend to protect the base of furniture and appliances.
- Product manufactured by the wet process.
- Product with Class I combustibility, according to NBR 15575.

September 05, 2017.
Cocal do Sul – SC – Brazil



Sergio Pereira Ruzza
Gerente de Tecnologia Cerâmica



Angela Waterkemper Vieira
Analista Desenvolvimento de Processos